

Extruded Graphite (EGK Series)

Feature:

Good mechanical, electrical & thermal properties / Low specific resistance / Relative fine grain size / Low ash content / Ease of precise machining

Applications:

Electrodes / Vacuum furnace / Heaters / Heat shields /Electronic tube anodes / Melting and sintering molds for various metals

EXTRUDED	EGK 1	EGK 2	EGK 3	EGK 4	EGK 5
Bulk Density (g/cc)	1.78	1.72	1.72	1.60	1.60
Max Grain Size	0.8mm	0.8mm	2 mm	0.8mm	2mm
Ash Content (PPM)	3000	3000	3000	3000	3000
Electrical Resistivity ($\mu\Omega\cdot m$)	≤ 7	≤ 8	≤ 8	≤ 8	≤ 8.5
Flexural Strength (MPa)	19	18	17	12	11
Compressive Strength (MPa)	47	45	44	32	30

Property Notes:

- Ash content of all grades can be purified to 50 PPM.
- Special property requirement specially produced.
- Density, mechanical strength and anticorrosion can be improved by further impregnations.

Size Capability:

Rods	Diameter	Length
Size Range	0-600mm	0-2500mm
Standard Size	50/75/100/200/300/400/500mm	1000/1800/2000mm

- Larger sizes available by special order.
- Machined parts done to drawings
- Anticorrosion cover available(SiC Cover, Pitch Cover, etc)

